

FORM PTO-1590 (Modified) (REV 11-98)		U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE		ATTORNEY'S DOCKET NUMBER D-43072-01-WO	
TRANSMITTAL LETTER TO THE UNITED STATES					
DESIGNATED/ELECTED OFFICE (DO/EO/US)					
CONCERNING A FILING UNDER 35 U.S.C. 371					
INTERNATIONAL APPLICATION NO. PCT/EP99/07338		INTERNATIONAL FILING DATE 04/10/99		U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR 1.5) 09/806812	
				PRIORITY DATE CLAIMED 19/10/98	

TITLE OF INVENTION
INTERFUSIBLE MULTILAYER POLYPROPYLENE FOAM SHEET

APPLICANT(S) FOR DO/EO/US
Gregorio DI CESARE and Renato COLNAGHI

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☐ This is an express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4. ☒ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
 - a. ☒ is transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ has been transmitted by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
- ☐ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
- ☒ A copy of the International Search Report (PCT/ISA/210).
- ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
 - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
 - b. ☐ have been transmitted by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☒ have not been made and will not be made.
- ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
- ☐ An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)).
- ☒ A copy of the International Preliminary Examination Report (PCT/IPEA/409).
- ☐ A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).

Items 13 to 20 below concern document(s) or information included:

13. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
14. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
15. ☐ A **FIRST** preliminary amendment.
16. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
17. ☐ A substitute specification.
18. ☐ A change of power of attorney and/or address letter.
19. ☐ Certificate of Mailing by Express Mail
20. ☐ Other items or information:

U.S. APPLICATION NO. (IF KNOWN) SEE 37 CFR 1.5	INTERNATIONAL APPLICATION NO.	ATTORNEY'S DOCKET NUMBER
09/806812	PCT/EP99/07338	D-43072-01-WO

21. The following fees are submitted:

BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)) :

<input type="checkbox"/> Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO	\$970.00
<input checked="" type="checkbox"/> International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO	\$840.00
<input type="checkbox"/> International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO	\$690.00
<input type="checkbox"/> International preliminary examination fee paid to USPTO (37 CFR 1.482) but all claims did not satisfy provisions of PCT Article 33(1)-(4)	\$670.00
<input type="checkbox"/> International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satisfied provisions of PCT Article 33(1)-(4)	\$96.00
ENTER APPROPRIATE BASIC FEE AMOUNT =	
Surcharge of \$130.00 for furnishing the oath or declaration later than months from the earliest claimed priority date (37 CFR 1.492 (e)).	<input type="checkbox"/> 20 <input type="checkbox"/> 30
	\$0.00

CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE	
Total claims	11 - 20 =	0	x \$18.00	\$0.00
Independent claims	3 - 3 =	0	x \$78.00	\$0.00
Multiple Dependent Claims (check if applicable).				<input type="checkbox"/> \$0.00
TOTAL OF ABOVE CALCULATIONS =				\$840.00
Reduction of 1/2 for filing by small entity, if applicable. Verified Small Entity Statement must also be filed (Note 37 CFR 1.9, 1.27, 1.28) (check if applicable).				<input type="checkbox"/> \$0.00
SUBTOTAL =				\$840.00
Processing fee of \$130.00 for furnishing the English translation later than months from the earliest claimed priority date (37 CFR 1.492 (i)).				<input type="checkbox"/> 20 <input type="checkbox"/> 30 + \$0.00
TOTAL NATIONAL FEE =				\$840.00
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) (check if applicable).				<input type="checkbox"/> \$0.00
TOTAL FEES ENCLOSED =				\$840.00
Amount to be refunded				\$
charged				\$

☐ A check in the amount of _____ to cover the above fees is enclosed.

☒ Please charge my Deposit Account No. **07-1765** in the amount of **\$840.00** to cover the above fees.
A duplicate copy of this sheet is enclosed.

☒ The Commissioner is hereby authorized to charge any fees which may be required, or credit any overpayment to Deposit Account No. **07-1765** A duplicate copy of this sheet is enclosed.

NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.

SEND ALL CORRESPONDENCE TO:

Law Department
Cryovac, Inc.
Post Office Box 464
Duncan,

SIGNATURE

THOMAS C. LAGALY

NAME

REGISTRATION NUMBER

DATE



I HEREBY CERTIFY THAT THIS CORRESPONDENCE
IS BEING DEPOSITED WITH THE UNITED STATES
POSTAL SERVICE AS FIRST CLASS MAIL, POSTAGE
PREPAID, IN AN ENVELOPE ADDRESSED TO:
COMMISSIONER FOR PATENTS,
WASHINGTON, D.C. 20231, ON THE DATE NOTED
BELOW MY SIGNATURE

Margaret B. White
Margaret B. White

6-26-01

DATE

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicants: Di Cesare et al

Serial No.: 09/806,812

Filing Date: April 3, 2001

Docket No.: D-43072-01

Title: THERMOFORMABLE MULTI-LAYER POLYPROPYLENE FOAM
SHEET

PRELIMINARY AMENDMENT

Commissioner for Patents
Washington, D.C. 20231

Sir:

This preliminary amendment is being filed in order to present the
claims of the above-identified application in better form for U.S.
examination. The application claims priority from European Application
No. 98119685.0, filed October 19, 1998, via International Application No.
PCT/EP99/07338, filed April 10, 1999.

IN THE CLAIMS


Please preliminarily amend claims 1-3, 7-8, and 10-11 to read as follows:

1. (Amended) A thermoformable, multilayer, co-extruded sheet comprising at least two separate foam polypropylene layers obtained by chemical foaming of two polypropylene resins having different flexural modulus.
2. (Amended) The thermoformable sheet of claim 1 wherein one of the two polypropylene resins is a "low modulus" polypropylene resin having a flexural modulus lower than 1,500 MPa.
3. (Amended) The thermoformable sheet of claim 1 wherein one of the two polypropylene resins is a "high modulus" polypropylene resin having a flexural modulus $\geq 1,500$ MPa.
7. (Amended) The thermoformable sheet of claim 1 wherein the gas barrier layer is bonded to said foam polypropylene layers by means of tie layers of modified polyolefins.
8. (Amended) The thermoformable sheet of claim 3, further comprising a heat-sealing layer adhered to an outer surface of the "high modulus" polypropylene foamed layer, said heat-sealing layer comprising one or more polymers having a melting point < 140 °C.
10. (Amended) The thermoformable sheet of claim 1, wherein said sheet has a density ranging from about 0.50 to about 0.85 g/cm³ and a flexural modulus higher than 400 MPa.

11. (Amended) A thermoformed article obtained from a sheet according to claim 1.

Attached hereto is a marked-up version of the changes made to the claims by the current amendment. Such attachment is captioned "VERSION WITH MARKINGS TO SHOW CHANGES MADE."

Respectfully submitted,



Thomas C. Lagaly
Attorney for Applicants
Registration No. 34,652

Scaled Air Corporation
P.O. Box 464
Duncan, SC 29334
(864) 433-2333

JUNE 26, 2001

Date

VERSION WITH MARKINGS TO SHOW CHANGES MADE

In the claims:

Claims 1-3, 7-8, and 10-11 have been amended to read as follows, wherein underlined terms have been added and bracketed terms have been deleted:

1. (Amended) A thermoformable, multilayer, co-extruded sheet comprising at least two separate foam polypropylene layers obtained by chemical foaming of two polypropylene resins having different flexural modulus[, a "high modulus" polypropylene and a "low modulus" polypropylene].

2. (Amended) The thermoformable sheet of claim 1 wherein [the] one of the two polypropylene resins is a "low modulus" polypropylene resin [has] having a flexural modulus lower than 1,500 MPa[, preferably \leq 1,400 MPa, and even more preferably \leq 1,300 MPa].

3. (Amended) The thermoformable sheet of claim 1 wherein [the] one of the two polypropylene resins is a "high modulus" polypropylene resin [has] having a flexural modulus \geq 1,500 MPa[, preferably \geq 1,650 MPa, and even more preferably \geq 1,800 MPa].

7. (Amended) The thermoformable[, multilayer, co-extruded] sheet of claim 1 [comprising at least two separate foam polypropylene layers obtained by chemical foaming of two different polypropylene resins having different flexural modulus, a "high modulus" polypropylene and a "low modulus" polypropylene, sandwiching a gas barrier layer comprising a polymer selected from the group consisting of ethylene-vinyl alcohol copolymers (EVOH), vinylidene chloride copolymers (PVDC), polyamides, and blends of

one or more EVOH and one or more polyamides,] wherein the gas barrier layer is bonded to said foam polypropylene layers by means of tie layers of modified polyolefins.

8. (Amended) The thermoformable [multilayer] sheet of claim [7] 3, further comprising a heat-sealing layer adhered [on the] to an outer surface of the "high modulus" polypropylene foamed layer, said heat-sealing layer comprising one or more polymers having a melting point < 140 °C], and preferably < 130 °C].

10. (Amended) [A] The thermoformable[, multi-layer, co-extruded, polypropylene foam having] sheet of claim 1, wherein said sheet has a density ranging from about 0.50 to about 0.85 g/cm³], preferably ranging from from about 0.60 to about 0.80 g/cm³] and a flexural modulus higher than 400 MPa.

11. (Amended) A thermoformed article obtained from a sheet according to [any of the preceding claims] claim 1.

THERMOFORMABLE MULTI-LAYER POLYPROPYLENE FOAM SHEET

The present invention relates to a multi-layer, co-extruded, thermoformable sheet suitable for the production of packaging material.

In particular the present invention relates to a co-extruded, rigid or semi-rigid, sheet comprising at least two polypropylene foam layers, said sheet being thermoformable into shaped articles for packaging.

Thermoforming is a common method for forming trays to be used in the packaging art for holding the products to be packaged. In some cases pre-formed trays are fed to a filling machine which inserts or lays the product to be packaged onto the tray and then either seals on a lid or wrap the loaded tray up. In most of the cases, particularly in the packaging of food products, e.g. fresh red meat or processed meat, a horizontal thermoform-fill-seal machine is employed. Said machine typically requires two separate webs of material, a lower or bottom web and an upper or top web. The lower web must be designed to be easily thermoformable as the machine creates a more-or-less shallow tray therefrom by pulling it across a heated cavity, or die, into which the sheet is drawn by vacuum at temperatures high enough to soften the sheet and allow it to adopt the shape of the cavity without tearing or cracking.

The sheet employed for this purpose therefore must have a good balance between thermoformability, as the speed of the thermoform-fill-seal machine is limited by the time required in the thermoforming step and the appearance of the end package will mainly depend on that of the supporting tray, and stiffness, as the tray should not bend during the packaging process or be distorted by the weight of the packaged product.

In some instances, when a lid is sealed to the tray or the tray rim, the lower web must also be heat-sealable. In some cases it is also required that said thermoformable sheet has a low permeability to gases, in particular oxygen, in order to prolong the shelf-life of oxygen susceptible products, e.g. most of the food products.

Other packaging machines, where an in-line thermoformable lower web is required, are those employed for skin packaging. In these machines the lower web is thermoformed into a tray, the product to be packaged is loaded thereon and the upper web is drawn down by

vacuum all around the product until the film conforms so faithfully to the product contours that it becomes like a skin. Also in this case a thermoformable sheet with a good balance between thermoformability and stiffness is required that preferably has gas barrier properties.

Cast solid sheets are typically employed for these applications. In some cases also foamed sheets are used, as the appearance of a foamed material is well appreciated in the market. One of the problems met with the foamed sheets is to obtain the desired balance between thermoformability and stiffness.

It is an object of the present invention to provide a rigid or semi-rigid foam sheet material that can suitably be thermoformed into a shaped container, such as a tray.

Another object of the present invention is to provide a thermoformable, multi-layer, co-extruded, polypropylene foam sheet having a density ranging from about 0.50 to about 0.85 g/cm³ and a flexural modulus higher than 400 MPa.

A still another object of the present invention is to provide a thermoformable foam sheet material co-extruded with a gas barrier layer for all those applications where a gas barrier packaging material is desired.

It has been found that the above objectives can be achieved by a multi-layer, co-extruded, sheet of thermoplastic material comprising at least two separate layers of foamed polypropylene obtained by chemically foaming polypropylene resins with different flexural modulus.

Polypropylene foam sheets comprising two different layers of foam polypropylene are described in WO 91/13933. More particularly said patent application describes polypropylene foam sheets obtained by physical foaming of a polypropylene resin with certain specific characteristics in terms of M_p , M_z/M_w ratio, J_e (equilibrium compliance) and/or S_f/S (recoverable shear strain per unit stress). The process there described is a physical process, i.e. a process where foaming is obtained by the use of a blowing agent such as a hydrocarbon, e.g. butane and isopentane, a chlorinated or chloro-fluorinated hydrocarbon, e.g. chloro-difluoromethane, or an inert gas such as nitrogen or carbon dioxide. Generally, however, the use of a hydrocarbon either or a blend of a hydrocarbon with an inert gas obtains physical

foaming. This creates problems of safety during the manufacturing process as well as during stocking of the foamed material. It is in fact necessary to age the foamed material in the warehouses until the trapped blowing gas is evolved and has been replaced by air. Forced ventilation of the warehouses is required and, depending also on the type of blowing agent employed, 5 to 7 days of aging are necessary before the foamed product can be distributed to customers.

WO 91/13933 also refers to the manufacture of a multi-layer foam sheet comprising a functional layer sandwiched between two polypropylene foam layers, possibly with tie layers bonding the foam polypropylene layer to the functional one. The process there schematically described provides for a co-extrusion where the same polypropylene material is foam extruded into two different layers and the foaming is always a physical foaming, with the drawbacks indicated above.

DETAILED DESCRIPTION OF THE INVENTION

A first object of the present invention is a thermoformable, multi-layer, co-extruded sheet comprising at least two separate foam polypropylene layers obtained by chemical foaming of two different polypropylene resins having different flexural modulus, a "high modulus" polypropylene and a "low modulus" polypropylene.

The flexural modulus of the "low modulus" polypropylene resin must be lower than 1,500 MPa, preferably $\leq 1,400$ MPa, and even more preferably $\leq 1,300$ MPa. Examples of "low modulus" polypropylene resins are for instance those commercially available from Montell as Polypropylene KF 6100 (Flexural Modulus, evaluated by ISO Standard Method 178, of about 1,300 MPa) and Polypropylene YX37F (Flexural Modulus of about 1,200 MPa).

The flexural modulus of the "high modulus" polypropylene resin must be $\geq 1,500$ MPa. Preferably it will be $\geq 1,650$ MPa, and even more preferably $\geq 1,800$ MPa. Examples of "high modulus" polypropylene resins are those commercially available from Montell as Adstif™ 680 ADXP (Flexural Modulus of 2,150 MPa) and Adstif™ 699 ADXP (Flexural Modulus of 1,950 MPa).

In the multi-layer co-extruded sheet of the present invention the two foam polypropylene

layers are separated by at least one substantially unfoamed layer. Any thermoplastic material or blend of thermoplastic materials can suitably be employed for said substantially unfoamed layer. The term "substantially unfoamed" is used herein to identify a layer that has not been submitted to a chemical foaming, i.e. that has not been admixed with a chemical foaming agent before extrusion. This term does not exclude, in particular for those layers that are directly adhered to the foam polypropylene layers, that the evolution of gas in the adjacent layers might give rise to a certain, non-substantial, foaming also in these layers.

In case the material or blend of materials used for said layer would not adhere to the foam polypropylene layers with a sufficient bond, tie or adhesive layers may be employed to increase said bond and prevent possible delamination problems.

In one preferred embodiment of the present invention recycle material is incorporated into said substantially unfoamed layer to give additional bulk to the sheet.

In a more preferred embodiment however said substantially unfoamed layer is a gas barrier layer, i.e. a layer of a suitably selected polymeric material and of the suitably selected thickness to provide for an overall multi-layer sheet with an oxygen permeability lower than $200 \text{ cm}^3/\text{m}^2.\text{day.atm}$, preferably lower than $150 \text{ cm}^3/\text{m}^2.\text{day.atm}$, more preferably lower than $125 \text{ cm}^3/\text{m}^2.\text{day.atm}$, and even more preferably lower than $100 \text{ cm}^3/\text{m}^2.\text{day.atm}$.

Suitable resins for use in said functional layer are preferably ethylene-vinyl alcohol copolymers (EVOH), vinylidene chloride copolymers (PVDC), polyamides, and blends of one or more EVOH with one or more polyamides.

As used herein, "EVOH" refers to ethylene-vinyl alcohol copolymers. EVOH includes saponified or hydrolyzed ethylene-vinyl acetate copolymers, and refers to vinyl alcohol copolymers having an ethylene comonomer content preferably comprised from about 28 to about 48 mole %, more preferably, from about 32 to about 44 mole % ethylene, and even more preferably, from about 38 to about 44 mole % ethylene, and a saponification degree of at least 85 %, preferably at least 90 %.

As used herein the term PVDC refers to a vinylidene chloride copolymer wherein a major amount of the copolymer comprises vinylidene chloride and a minor amount of the copolymer

comprises one or more unsaturated monomers copolymerisable therewith, typically vinyl chloride, and alkyl acrylates or methacrylates (e.g. methyl acrylate or methacrylate) or to a blend thereof in different proportions. Generally said PVDC contains plasticisers and/or stabilisers as known in the art.

As used herein, the term polyamide is intended to refer to both polyamides and co- or terpolyamides. This term specifically includes aliphatic polyamides or co-polyamides, aromatic polyamides or co-polyamides, and partially aromatic polyamides or co-polyamides, modifications thereof and blends thereof.

In case one of the above gas barrier materials is employed for the substantially unfoamed layer, tie layers will be present to increase the bond between said layer and the foam polypropylene ones. Suitable tie layers will preferably comprise modified polyolefins, and more preferably modified polypropylene, modified polyethylene, and modified ethylene copolymers, such as modified ethylene- α -olefin copolymers, and modified ethylene-unsaturated ester copolymers, e.g. modified ethylene-vinyl acetate copolymers.

As used herein the term "modified", when referred to any polyolefin, is inclusive of modified polymer prepared by copolymerizing the homopolymer of the olefin or copolymer thereof with an unsaturated carboxylic acid, e.g., maleic acid, fumaric acid or the like, or a derivative thereof such as the anhydride, ester or metal salt or the like; or by incorporating into the olefin homopolymer or copolymer, an unsaturated carboxylic acid, e.g., maleic acid, fumaric acid or the like, or a derivative thereof such as the anhydride, ester or metal salt or the like. Examples of suitable modified polyolefins are in particular polymers having an anhydride functionality, as defined above, grafted thereon and/or copolymerized therewith and/or blended therewith, wherein preferably, such modified polymers have the anhydride functionality grafted on or polymerized therewith, as opposed to merely blended therewith.

In a preferred embodiment the present invention relates to a thermoformable, multi-layer, co-extruded sheet comprising at least two separate foam polypropylene layers obtained by chemical foaming of two polypropylene resins having different flexural modulus, a "high modulus" polypropylene and a "low modulus" polypropylene, sandwiching a gas barrier layer

comprising a polymer selected from the group consisting of ethylene-vinyl alcohol copolymers (EVOH), vinylidene chloride copolymers (PVDC), polyamides, and blends of one or more EVOH and one or more polyamides, bonded to said foam polypropylene layers by means of tie layers.

5 The thickness of the overall thermoformable sheet of the present invention is typically comprised between about 400 and about 1,300 μm . For most of the conventional applications a preferred thickness is in the range of from about 500 to about 1,000 μm , with a most preferred thickness in the range of from about 600 to about 900 μm .

The thickness of each of the foamed polypropylene layers may range from about 100 to about 700 μm , and is preferably comprised between about 150 and about 550 μm , and more preferably between about 200 and about 400 μm . Generally the optimum thickness of the "low modulus" and of the "high modulus" polypropylene layers and their ratio depends on the numerical values thereof and could be easily determined, by trial and error, bearing in mind that the flexural modulus of the end multi-layer sheet should be higher than 400 MPa, preferably higher than 500 MPa, and even more preferably higher than 600 MPa.

When the substantially unfoamed layer separating the two polypropylene foam layers is not a functional layer, its thickness is not critical. Layers as thin as few μm 's or as thick as 250, 300, 350, or more μm can be present.

20 When the substantially unfoamed layer is a functional layer, its thickness is generally controlled and comprised between about 5 and about 50 μm , preferably between about 6 and about 40 μm , and even more preferably between about 7 and about 30 μm . The thickness of said functional layer should in fact be high enough to guarantee the desired maximum oxygen permeability of the end sheet, but, mainly in view of the cost of the raw polymers, should not be considerably higher than that.

25 The thickness of the tie layers, as usual, will be limited to few μm 's i.e. what is generally needed to provide for the desired bond. As foaming does modify the polymer surface at the interface with the adjacent layers, it is generally required a slightly higher thickness of the tie layers with respect to the corresponding unfoamed structure, e.g. typically up to about 20 μm .

Even when an end sheet is obtained wherein the two foamed polypropylene layers are both outer layers, the structure is not symmetrical owing to the different modulus of the two polypropylene layers. Thermoforming of this structure needs to be carried out in such a way that the "low modulus" polypropylene layer is the layer in contact with the die cavity and the "high modulus" polypropylene layer is the upper layer in direct contact with the product to be packaged.

When the thermoformable sheet according to the present invention is used in a packaging process that comprises sealing of an upper web or lid to the tray surface, it would be highly desirable to have a heat-sealing layer adhered on the outer surface of the foamed "high modulus" polypropylene layer.

As used herein the term "adhered", as applied to sheet layers, includes both direct adherence of the subject layer to the other layer referred to or to the other two layers the subject layer is between, as well as a lack of direct adherence, i.e., one or more additional layers can be imposed between the subject layer and the other layer referred to or between the subject layer and one or both of the layers the subject layer is between.

Such a heat-sealing layer would be a layer of a substantially unfoamed, heat-sealable resin or blend of resins, and will provide for an improved heat-sealability of the overall structure.

Said heat-sealing layer will be the upper layer in the end sheet, i.e. the layer that in the tray will be supporting the product to be packaged and will be in direct contact therewith.

Suitable heat-sealing polymers preferably have a melting point $< 140^{\circ}\text{C}$, and preferably $< 130^{\circ}\text{C}$. Such a heat-sealing layer will typically comprise polyethylene homopolymers; heterogeneous or homogeneous ethylene-($\text{C}_4\text{-C}_8$)- α -olefin copolymers having a density $\leq 0.915 \text{ g/cm}^3$; blends thereof with minor amount of polyethylene homopolymers; ethylene-vinyl acetate copolymers; ethylene-acrylic or methacrylic acid copolymers including ionomers; heterogeneous or homogeneous ethylene-($\text{C}_4\text{-C}_8$)- α -olefin copolymers having a density from about 0.915 g/cm^3 to about 0.930 g/cm^3 ; blends thereof with ethylene-vinyl

acetate copolymers or ethylene-alkyl (meth)acrylate copolymers; ethylene-propylene-butene ter-polymers; ethylene-alkyl acrylate-maleic anhydride ter-polymers; and the like polymers.

If necessary or desirable, a tie layer will be present to bond the heat-sealing layer to the polypropylene foam one.

5 In a preferred embodiment of the present invention the thermoformable, multi-layer, co-extruded sheet may also comprise an easy opening feature.

As an example, the heat-sealing layer of the thermoformable sheet may comprise a so-called "peelable" blend. When the thermoformed bottom web, bearing said peelable blend in the upper heat-sealing layer, is sealed to a suitably selected top web, easy opening of the end package is then obtained by separating the two webs at the seal interface by a peeling mechanism.

Alternatively a thin heat-sealing layer may be adhered directly to the foamed polypropylene or to a layer of a polymer with which it has a low bond. In this case the easy opening of the package is obtained by first breaking through the thickness of the thin heat-sealing layer and then delaminating said heat-sealing layer from the underlying support or film.

Still alternatively the easy opening feature is provided by the use of a layer of a blend of only partially compatible polymers having a low internal cohesion. Said low cohesion layer may possibly be coated with a thin heat-sealing layer. Opening of the package in such a case
20 is achieved by internal rupture of the low cohesion layer (and if present of the thin heat-sealing layer first). Examples of blends useful in this alternative easy opening system are described for instance in EP-B-192,131.

It is not necessary that at least one of the outer layers of the thermoformable sheet of the present invention be a layer of "low modulus" foamed polypropylene. It is in fact also
25 possible to coat said polypropylene layer, still by a co-extrusion process, with one or more layers of a thermoplastic foamed or solid material or blend of materials. Said additional layer(s) may be useful for instance to improve the appearance or the properties of the thermoformable sheet, e.g. providing a paper-like appearance or a colored/metallised

appearance or providing the thermoformable sheet with UV absorbing properties, antistatic properties, or slip properties. As the "low modulus" foamed polypropylene layer is always closer to the die cavity than the "high modulus" one, the material that will be present in the outer layer adhered to said "low modulus" foamed polypropylene layer should be selected in such a way to withstand direct contact with the heated cavity die during thermoforming.

One of the advantages of the thermoformable sheet according to the present invention is that it can be obtained by co-extrusion, using a flat die. The use of a flat die and of the flat sheet technology, providing for the calendaring of the flat multilayer sheet following extrusion and quenching, allows a better thickness control of the end sheet. An annular die, as required in the physical foaming processes, could however be employed also in this case.

Chemical foaming of the propylene layers is obtained by extruding the resins admixed with the suitable amount of a chemical blowing agent, preferably an endothermic chemical blowing agent.

A chemical foaming agent is a chemical or compound that reacts or decomposes at elevated temperatures, such as those employed in extrusion, to give a product that is normally a gas at atmospheric pressure. The most common chemical foaming agent is sodium bicarbonate with a small amount of citric or tartaric acid as a co-agent. These agents are typically in dry powder form and are dusted or master-batched into the thermoplastic pellets prior to introduction into the extrusion equipment. Proprietary alkali carbonate mixtures suitable as chemical foam agents are those commercialised by Boehringer Ingelheim under the trade name Hydrocerol™ or by Hoechst Celanese under the trade name Hostatron™. Generally these products are sold in the form of master-batches containing about 40 % of foaming agent and said master-batches are added to the polypropylene pellets in an amount typically comprised between about 0.2 and about 3.0 % by weight, preferably between about 0.5 and about 2 % by weight. In the co-extrusion process for the manufacture of the thermoformable sheet according to the present invention, the two polypropylene resins need not to contain the same foaming agent or the same amount of foaming agent. Typically the amount of foaming master-batch in a core polypropylene layer will be comprised between

about 0.5 and about 1.5 % by weight, while it will be comprised between about 1 and about 2.5 % by weight if the foamed polypropylene layer is an outer layer.

The invention may be further understood by reference to the following examples that are provided for the purpose of representation and are not to be construed as limiting the scope of the invention. Unless stated otherwise, all percentages, parts, etc. are by weight.

Example 1

The following resins have been co-extruded through a flat die in the sequence reported below. The layer number 1. is the sheet layer that in the thermoforming process is in contact with the heated cavity die. The thickness of each layer in the end partially foamed sheet is also reported between parentheses :

1. Low flexural modulus polypropylene (Montell YX37F sold by Montell – flexural modulus of about 1,200 MPa) blended with 2 % by weight of Hydrocerol™ CF 40 E (350 µm);
2. Modified ethylene-vinyl acetate copolymer (Orevac™ 18211 sold by Elf Atochem) (15 µm);
3. Ethylene-vinyl alcohol copolymer (EVALC F-101 BZ sold by Kuraray) (21 µm);
4. Modified ethylene-vinyl acetate copolymer (Orevac™ 18211 sold by Elf Atochem) (15 µm);
5. High flexural modulus polypropylene (Adstif™ 699 ADXP sold by Montell – flexural modulus of about 1950 MPa) blended with 1 % by weight of Hydrocerol™ CF 40 E (260 µm);
6. Modified ethylene-vinyl acetate copolymer (Orevac™ 18211 sold by Elf Atochem) (20 µm);
7. Blend of 66 % by weight of ionomer (Surlyn™ 1601 sold by DuPont), 24 % by weight of modified ethylene-vinyl acetate copolymer (Elvaloy™ 741A sold by DuPont), and 10 % of polybutene (Polybutene 8640 sold by Shell) (12 µm);
8. Ethylene-vinyl acetate copolymer (Escorene™ UL00909 sold by Exxon) (7 µm).

The co-extruded sheet has been quenched on a chill roll and calendered.

Flexural modulus of the end sheet was about 850 MPa in MD (machine direction) and about 750 MPa in TD (transverse direction).

The density of the end sheet was about 0.7 g/cm³.

Oxygen permeability of the obtained structure was about 1-2 cm³/m².day.atm, when
5 measured at 23 °C and 0 % R. H. according to ASTM D3985.

The thermoformability in-line of the obtained sheet was tested on a Multivac CD 6000 machine for Vacuum Skin Packaging. The thermoforming conditions were as follows :

- forming temperature : 150 °C (with sandwich plate)
- forming pressure : 2.5 bar
- 10 - heating time : 5 seconds
- forming depth : 5 mm, 20 mm, and 27 mm.

In all the three depths tested the results were very good and both corners and grooves were very well defined with no creases or cracks.

00006612.076204

CLAIMS

1. A thermoformable, multilayer, co-extruded sheet comprising at least two separate foam polypropylene layers obtained by chemical foaming of two polypropylene resins having different flexural modulus, a "high modulus" polypropylene and a "low modulus" polypropylene.
2. The thermoformable sheet of claim 1 wherein the "low modulus" polypropylene resin has a flexural modulus lower than 1,500 MPa, preferably $\leq 1,400$ MPa, and even more preferably $\leq 1,300$ MPa.
3. The thermoformable sheet of claim 1 wherein the "high modulus" polypropylene resin has a flexural modulus $\geq 1,500$ MPa, preferably $\geq 1,650$ MPa, and even more preferably $\geq 1,800$ MPa.
4. The thermoformable sheet of claim 1 wherein at least one substantially unfoamed layer is positioned between the two foam polypropylene layers.
5. The thermoformable sheet of claim 4 wherein the substantially unfoamed layer is a gas barrier layer.
6. The thermoformable sheet of claim 5 wherein the gas barrier layer comprises a polymer selected from the group consisting of ethylene-vinyl alcohol copolymers (EVOH), vinylidene chloride copolymers (PVDC), polyamides, and blends of one or more EVOH and one or more polyamides.
7. The thermoformable, multilayer, co-extruded sheet of claim 1 comprising at least two separate foam polypropylene layers obtained by chemical foaming of two different polypropylene resins having different flexural modulus, a "high modulus" polypropylene and a "low modulus" polypropylene, sandwiching a gas barrier layer comprising a polymer selected from the group consisting of ethylene-vinyl alcohol copolymers (EVOH), vinylidene chloride copolymers (PVDC), polyamides, and blends of one or more EVOH and one or more polyamides, bonded to said foam polypropylene layers by means of tie layers of modified polyolefins.

8. The thermoformable multilayer sheet of claim 7 further comprising a heat-sealing layer adhered on the outer surface of the "high modulus" polypropylene foamed layer, said heat-sealing layer comprising one or more polymers having a melting point $< 140^{\circ}\text{C}$, and preferably $< 130^{\circ}\text{C}$.
- 5 9. The thermoformable multi-layer sheet of claim 8 wherein the heat-sealing layer comprises a polymer selected from the group consisting of polyethylene homopolymers; heterogeneous or homogeneous ethylene-($\text{C}_4\text{-C}_8$)- α -olefin copolymers having a density $\leq 0.915 \text{ g/cm}^3$; blends thereof with minor amount of polyethylene homopolymers; ethylene-vinyl acetate copolymers; ethylene-acrylic or methacrylic acid copolymers including ionomers; heterogeneous or homogeneous ethylene-($\text{C}_4\text{-C}_8$)- α -olefin copolymers having a density from about 0.915 g/cm^3 to about 0.930 g/cm^3 ; blends thereof with ethylene-vinyl acetate copolymers or ethylene-alkyl (meth)acrylate copolymers; ethylene-propylene-butene ter-polymers; ethylene-alkyl acrylate-maleic anhydride ter-polymers; and the like polymers.
- 10 10. A thermoformable, multi-layer, co-extruded, polypropylene foam sheet having a density ranging from about 0.50 to about 0.85 g/cm^3 , preferably ranging from from about 0.60 to about 0.80 g/cm^3 and a flexural modulus higher than 400 MPa .
- 15 11. A thermoformed article obtained from a sheet according to any of the preceding claims.



I HEREBY CERTIFY THAT THIS CORRESPONDENCE IS BEING DEPOSITED WITH THE UNITED STATES POSTAL SERVICE AS FIRST CLASS MAIL SERVICE, POSTAGE PREPAID, IN AN ENVELOPE ADDRESSED TO: COMMISSIONER FOR PATENTS, WASHINGTON, D.C. 20231, ON THE DATE NOTED BELOW MY SIGNATURE.

Margaret B. White

Margaret B. White

6-26-01

DATE

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicants: Di Cesare et al

Docket No.: D-43072-01 US

International Application No.: PCT/EP99/07338

Serial No.: 09/806,812

U.S. Filing Date: 04-03-01

Title: THERMOFORMABLE MULTI-LAYER POLYPROPYLENE FOAM SHEET

COMBINED DECLARATION AND POWER OF ATTORNEY-PLURAL INVENTORS

Sir:

As the above-identified inventors, we hereby declare that:

- 1) Our respective residence and post office address and citizenship are given below.
- 2) We believe that we are the first, original, and joint inventors of the subject matter which is claimed and for which a patent is sought for the above-entitled invention, the specification of which was filed in the U.S. on April 3, 2001, with application number 09/806,812. ✓
- 3) We have reviewed and understand the contents of the above-identified specification, including the claims and any drawings attached thereto.
- 4) We acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations 1.56(a).
- 5) Pursuant to 35 U.S.C. 119, we hereby claim foreign priority benefits based upon the below-identified foreign application for patent or inventor's certificate:

Country: European Patent Office ✓
Serial No.: 98119685.0 ✓
Filed: October 19, 1998 ✓

- 6) Any corresponding foreign counterpart applications for patent or inventor's certificate which were filed prior to the above-identified priority application are listed below:

Country: N/A
Serial No.: N/A
Filed: N/A

- 7) I hereby appoint the following attorneys who may be reached at the below-identified address and telephone numbers, to prosecute this application and to transact all business in the Patent and Trademark Office connected herewith: John J. Wasatonic, Registration No. 29,984, Mark B. Quatt, Registration No. 30,484; Rupert B. Hurley Jr., Registration No. 29,313, Thomas C. Lagaly, Registration No. 34,652 and Daniel B. Ruble, Registration No. 40,794.

Direct all correspondence and telephone calls to Thomas C. Lagaly at:

Address: Cryovac, Inc.
P. O. Box 464
Duncan, SC 29334
Telephone: (864) 433-2333

- 8) All statements made herein of my own knowledge are true and all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

1-00 FULL NAME OF INVENTOR: Gregorio Di Cesare
INVENTOR'S SIGNATURE: Gregorio Di Cesare
DATE OF EXECUTION: 21/6/02
CITIZENSHIP: Italian
RESIDENCE ADDRESS: Via XX Settembre 81 - 20023 Cerro Maggiore
(Milan) - Italy ITX
POST OFFICE ADDRESS: _____

2-00

FULL NAME OF INVENTOR:

Renato Angelo Colnaghi

INVENTOR'S SIGNATURE:

Renato Angelo Colnaghi

DATE OF EXECUTION:

22/08/2004

CITIZENSHIP:

Italian

RESIDENCE ADDRESS:

Via Europa 18/B
20010 Pogliano Milanese
(Milan) Italy IT .

POST OFFICE ADDRESS:

09906512.070201
102020.2199080